

ENVIROCRETE™

General Purpose Concrete



DESCRIPTION

Envirocrete contains a mix of recycled concrete aggregate, sand, fly ash and cement. This is suitable for all general purpose concreting applications where a quality concrete is required.

This product contains 50% recycled material.

RECOMMENDED USE

Concrete projects 40mm thick or more. For building anything out of concrete, including:

- Foundation walls and footings
- Sidewalks, curbs, steps, ramps and walkways
- Appliance and equipment platforms
- Pipe and post footings
- Floor slabs and patios
- Pools, fish pools, stepping stones & bird baths
- Slope protection
- Driveways

CLARIFICATION

Other than the fact that the contents in ENVIROCRETE contain 50% recycled material, the environmental impact of this product is in no way different from standard concrete containing no recycled material. Due care needs to be taken in disposing unused product and it should not enter our waterways which adversely affects our environment. Keep this product out of sewers and stormwater and follow your local council guidelines for usage and disposal.

PACKAGING

- 15kg bags
- Bulk bags available

YIELD

One 15kg bag will approximately produce a slab equivalent to 600 x 300 x 40mm (0.0072 cubic metres).

DIRECTIONS FOR USE

1. Empty contents into a wheelbarrow or mechanical mixer or onto a smooth non-porous surface or use CEMIX EZY CONCRETE MIXING BAG.
2. Add water gradually, mixing thoroughly until a workable mix is achieved..
3. Use mixed concrete immediately, do not allow to stand.
4. Damp the sub grade before concrete is placed.

5. Upon placing the concrete at site, work sufficiently to remove air voids if any and compact well with a tamping rod working into all areas.
6. Level off the corners and finish flat with a wooden float for coarse finish or a steel trowel for a smooth finish.
7. Use CEMIX CONCRETE CURE WB to cure concrete, or just keep the surface damp for the first seven days.
8. Spray CEMIX FORM RELEASE on all framing/boxing for an easy release with fine edging.

TECHNICAL DATA

After 7 days the concrete will achieve a minimum strength of 17MPa and 28MPa after 28 days.

STORAGE

Store all cement products in a cool dry area and use within 6 months.

WARNINGS

HAZARDOUS - PORTLAND AND BLENDED CEMENT
This product may contain Crystalline Silica.

RISK: Cements may cause respiratory, skin and eye irritation. Wet cement can be irritating and corrosive to eyes and skin; and may cause skin sensitization (dermatitis). Repeated inhalation may cause bronchitis, silicosis and lung cancer and increase risk of scleroderma.

SAFETY: Avoid contact with eyes and skin, both from wet and dry mix. Do not breathe in dust. Wear suitable protective clothing, gloves, eye protection and barrier cream. Wear a suitable dust mask. Wash thoroughly after handling and properly store any leftover material.

FIRST AID: Irrigate eyes with plenty of water and seek medical advice immediately.

SPILLS AND LEAKS : Keep out of sewers and stormwater drains and dispose of any leftover material as trade waste in accordance with local authority guidelines. Additional information can be had from the brochures or by calling 0800 ASK CEMIX.

DISCLAIMER

Please Note: Recommendations and advice regarding the use of this product are to be taken as a guide only. Other than as appears on this product's packaging, CEMIX LTD does not give any warranty express or implied as to the suitability of this product for your particular use, because the usage of this product is beyond the control of CEMIX LTD. If you need advice concerning the use of suitability of this product for your particular application, please contact CEMIX LTD first. If this product is defective because of CEMIX LTD's fault, please contact the supplier or CEMIX LTD. who will replace it at no cost.