

MORE THAN CONCRETE

1/2



EASYPLI

GENERAL MORTAR PLASTICISER

AVAILABLE SIZES: 250gm, 700gm, 1.2kg, 2.5kg, 10kg & 40kg



DESCRIPTION

CEMIX® EASYPLI powder has been formulated especially for the bricklayer and block layer who is looking for a high yield, low cost, plasticiser using a combination of non-toxic, non-staining chemical powders. CEMIX® EASYPLI will meet the needs of the tradesman by giving good extension to board life, excellent workability, good hold on the trowel and reduces water content. CEMIX® EASYPLI meets the requirements of NZSS and ASTM when used in accordance with directions for dosage and mixing.

TYPICAL APPLICATION/USES

CEMIX® EASYPLI can be used for all Portland cement/sand mortars for bricklaying, block laying and plastering. The addition of lime and admixtures is not needed. This product can be used for coloured mortars including black oxide and white cement.

ADVANTAGES

- Easy to use powder
- Reusable watertight container
- Cost effective
- Longer board life
- Non-staining
- Excellent hold
- Increased bond strength
- Use on all sand types
- Reduces shrinkage and cracking
- Works well with colours and oxides

SUBSTRATE PREPARATION

It is important to ensure the substrate surface is clean and free from dust and loose material. Old paint should be removed, as should oil, grease, wax, curing compounds and surface laitance etc. Substrate surfaces should be pre dampened with water, with

any excess brushed off.

MIXING

Add CEMIX® EASYPLI to 2/3 of water in mixer, add 1/2 sand then cement, add remaining sand and balance of water to required consistency. There is no need to over mix mortar, a maximum of 5 minutes should be sufficient. To hand mix add and mix CEMIX® EASYPLI to a small amount of water, mix into dry sand/cement mixture, then add water to desired consistency.

COVERAGE

Use at a rate of 30gm / 40kg bag of Portland cement. Usage is dependant on the sand or cement type and condition. More or less can be used to suit but do not overdose. Each container of CEMIX® EASYPLI will plasticise the following amount of bags of cement (40kg)

250gms = 8 bags 700gms = 23 bags 1.2kg = 40 bags 2.5 kg = 83 bags10kg = 333 bags

PACKAGING

250gm, 700gm, 1.2kg, 2.5kg and 40kg pail. A 10gm measure is provided in each container.

STORAGE & SHELF LIFE

Store in dry place and shake well before use.

CLEANING

Clean all tools with water & brush immediately after use.



2/2

EASYPLI

TECHNICAL DATA

APPEARANCE:

Cream Powder

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations may occur on site.

If medical advice is needed, have product container or label at hand. Read label before use. Keep out of reach of children.





HAZARD STATEMENTS

- Causes skin irritation
- Causes serious eye damage

PREVENTION

Wear protective gloves/protective clothing/eye protection/ face protection

RESPONSE

- IF IN EYES: Rinse cautiously with water for several minutes Remove contact lenses, if present and easy to do. Continue
- Immediately call NZ POISON CENTER (0800 764 766) or doctor/physician
- Take off contaminated clothing and wash before reuse
- IF ON SKIN: Wash with plenty of soap and water
- If skin irritation occurs: Get medical advice/attention

STORAGE

Not applicable

DISPOSAL

Not applicable

DISCLAIMER

Please Note: Recommendations and advice regarding the use of this product are to be taken as a guide only. Other than as appears on this product's packaging, CEMIX® PRODUCTS LTD does not give any warranty express or implied as to its suitability for any particular use. For all advice concerning the use of, or suitability of this product for a particular application please contact CEMIX® PRODUCTS LTD. If this product is defective, please contact the merchant the material was purchased from or CEMIX® PRODUCTS LTD who will refund or replace it in accordance with the requirements of the Consumer Guarantees Act.

SCAN QR CODE FOR MORE PRODUCT INFORMATION.



CEMIX® PRODUCTS LTD

19 ALFRED STREET ONEHUNGA 1061 AUCKLAND NEW ZEALAND 0800 ASK CEMIX I +64 09 636 1000 WWW.CEMIX.CO.NZ



Twitter/CemixNZ



Facebook/CemixNz



Pintrest/CemixNZ



YouTube/CemixVideos

