



MAXCRETE

HIGH STRENGTH CONCRETE



20kg

APPLICATION:

Empty contents into a wheelbarrow or mechanical mixer or onto a smooth non-porous surface. Add water gradually, mixing thoroughly until a workable mix is achieved. Under ideal conditions a bag of a 20kg bag would require 2.0 litres of water. Use the mixed concrete immediately, do not allow to the mix to stand. Dampen the substrate before the concrete is placed. Upon placing the concrete at site, work sufficiently to remove air voids if any and compact well with a tamping rod working into all areas. Level off the corners and finish flat with a wooden float for coarse finish or a steel trowel for a smooth finish. Use Cemix® Concrete Cure WB to cure concrete, or just keep the surface damp for the first 7 days.

DESCRIPTION:

Cemix® Maxcrete is suitable for any project requiring high early strength (light traffic within 8 hours) and faster set times. It consists of a uniformly blended, properly proportioned mixture of aggregate, sand, Portland cement and admixtures approved for use in concrete to improve workability and performance of the product. It is generally used for foundation walls and footings, footpaths, kerbs, steps, ramps and walkways in high traffic areas, appliance and equipment platforms, pipe and post footings, truck access area, and infrastructure areas.

TYPICAL APPLICATION/USES:

It is generally used for:

- Foundation walls and footings
Footpaths, kerbs, steps, ramps and walkways in high traffic areas
- Appliance and equipment platforms
- Pipe and post footings
- Truck access area
- Playground equipment
- School areas
- Infrastructure areas

ADVANTAGES:

- Premixed
- Computerised batching for uniform strength and consistency
- Easy to use, just add water.
- High early strength
- High final strength of 35 mpa

SUBSTRATE PREPARATION:

Typically compacted hardfill prior to pour. Before pouring, ensure the surfaced is dampened with water.

MATERIALS:

Cemix® Maxcrete consists of a uniformly blended, properly proportioned mixture of aggregate, sand, Portland cement and other Cemix® proprietary admixtures approved for use in concrete to improve workability and performance of the product.

PRECAUTION:

HAZARDOUS – PORTLAND AND BLENDED CEMENT . This product may contain Crystalline Silica. Cements may cause respiratory, skin and eye irritation. Wet cement can be irritating and corrosive to eyes and skin; and may cause skin sensitization (Dermatitis). Repeated inhalation may cause bronchitis, silicosis and lung cancer and increase risk of scleroderma.

SAFETY:

Avoid contact with eyes & skin, both from wet & dry mix. Do not breathe in dust. Wear suitable protective clothing, gloves, eye protection & barrier cream. Wear a suitable dust mask. Wash thoroughly after handling & store any leftover material properly.

CEMIX® PRODUCT LTD
19 ALFRED STREET
ONEHUNGA 1061
AUCKLAND
NEW ZEALAND

0800 ASK CEMIX
WWW.CEMIX.CO.NZ



TECHNICAL DATA:

APPEARANCE:	Grey Cementitious
APPLICATION TEMP:	5°C - 30 °C
STRENGTH:	10MPa @ 1 day, 17MPa @ 3 days, 25MPa @ 7 days, 35MPa @ 28 days.
<i>The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations may occur on site.</i>	

COVERAGE:

1 x 20kg bag approximately 0.0096m³.

PACKAGING:

Cemix[®] Maxcrete is available in 20kg bag.

STORAGE & SHELF LIFE:

Cemix[®] Maxcrete in a cool dry area. Use within six (6) months.

CLEANING:

Clean all tools with water & brush immediately after use.

SPILLS AND LEAKS:

Keep out of sewers & storm water drains & dispose of any leftover material as trade waste in accordance with local authority guidelines.

DISCLAIMER:

Please Note: Recommendations and advice regarding the use of this product are to be taken as a guide only. Other than as appears on this products packaging, Cemix[®] Products LTD. does not give any warranty express or implied as to the suitability of this product for your particular use, because the usage of this product is beyond the control of Cemix[®] Products LTD. If you need advice concerning the use of suitability of this product for your particular application, please contact Cemix[®] Products LTD first. If this product is defective because of Cemix[®] Products LTD's fault, please contact the supplier or Cemix[®] Products LTD. who will replace it at no cost.

CEMIX[®] PRODUCT LTD
19 ALFRED STREET
ONEHUNGA 1061
AUCKLAND
NEW ZEALAND
0800 ASK CEMIX
WWW.CEMIX.CO.NZ

